



 **WESTEX INC.**
A WORLD LEADER IN FLAME RESISTANT FABRICS

www.westexinc.com

INDURA

Ultra Soft

Flame Resistant Fabrics



Protection. Comfort. Value.

INDURA®

Ultra Soft

Flame Resistant Fabrics

- **Guaranteed Flame Resistance**
- **New Softer Feel** 
- **50%+ Extended Garment Wear Life**
- **Enhanced Protection**
- **Multi-Purpose Protection**
- **Excellent Value Equation**

The flame resistance of the fabric is guaranteed for the useful life of the garment provided the manufacturer's recommendations are followed. Following these procedures maximizes the appearance and service life of the garment.

INDURA® Ultra Soft® is a trademark of Westex Inc.

LAUNDERING INSTRUCTIONS

WASHING

1. Do not overload washer.
2. Use high water level.
3. Wash at temperature necessary to clean garment.
(maximum 165°F, or 74°C)
4. Use recommended amount of quality detergent. (Phosphate can be used.)
5. **Do not use chlorine bleach or hydrogen peroxide either separately or in detergents.**
6. Do not use softeners or starch.
7. Do not use tallow soap, i.e., one containing animal fats.
8. For optimum results when industrial laundering, use an acid sour.
9. Softened water provides best results.

DRYING

1. Do not use extreme heat or leave in for long periods.
(Maximum stack temperature 165°F, or 74°C)
2. The basket temperature should not exceed 280°F, or 138°C.
3. Remove garment immediately when dry or when slightly damp. Complete drying on a hanger. Overdrying will result in excessive shrinkage.
4. Garments may be line dried.

PRESSING

1. Garments may be pressed to remove wrinkles.
2. Use cotton setting.

Clean garment thoroughly. Failure to launder properly could adversely affect the flame resistance of the fabric. A complete cleaning guide can be found at www.westexinc.com.